Quimser S.A.
Leather Chemical Products
www.quimser.com
+34 938 032 688
info@quimser.com
C/Lleida, 39
08711 Òdena, Barcelona (Spain)

SERCRYL A-450

RESINAS ACRÍLICAS

Especificaciones:

Composición química:

Polimeros naturales. Acrilats, emulsionants, aigua i additius.

Aspecto:

Líquido fluido.

Color:

Amarillento.

pH:

9,0±1,0

% Materia activa

20±1%

Solidez a la luz:

Excelente

Carga:

Aniónico

Tiempo de vida:

Debidamente almacenados (+5 Y +35ºC) tienen una duración mínima de 6 meses.

Propiedades generales:

Resina acrílica de anclaje. Films ligeros y elásticos. Mejora la penetración y adhesión de las capas de fondo.
Muy adecuada para impregnaciones debido a su partícula fina.

Dosis de aplicación:

Las dosis varian según el tipo de acabado requerido. Aplicar en capas de fondo entre 300-500 g/L

Quimser complies with the European standards.
All data and recommendations herein are accurate at the time of publication. QUIMSER S.A. reserves the right to modify them without notice. Work conditions and type of raw material can effect the final results. It is the responsibility of the user to apply the recommendations to the actual conditions and particular purpose.